DERWENT-ACC-NO:

1979-41535B

DÉRWENT-WEEK:

197922

COPYRIGHT 2006 DERWENT INFORMATION LTD

TITLE:

Aq. coating dispersions with good heat sealing

and

antiblocking - comprise copolymer of ethylene!

and

2,3-unsatd. carboxylic acid partly in salt

form, and wax

PATENT-ASSIGNEE: ASAHI DOW LTD [ASAF]

PRIORITY-DATA: 1977JP-0116136 (September 29, 1977)

PATENT-FAMILY:

PUB-NO

PUB-DATE

**LANGUAGE** 

PAGES

MAIN-IPC

JP 54050531 A

April 20, 1979

N/A

000

N/A

INT-CL (IPC): C09D003/74, C09D005/00

ABSTRACTED-PUB-NO: JP 54050531A

BASIC-ABSTRACT:

Aq. coating dispersion is obtd. by dispersing (1) 100 pts. wt. of the

copolymers comprising 99-85 mole % of  $\underline{\text{ethylene}}$  and 1-15 mole % of alpha,

beta-ethylene unsatd. carboxylic acids of which >=10% has been neutralised

with metal ions and/or ammonium ion and (2) 0.5-5.0 pts. wt. of waxes in a solid content of 20-60 wt.%.

The dispersions have excellent heat-sealing property and **blocking** resistance.

The alpha, beta-ethylene unsatd. carboxylic acids include, e.g. acrylic acid,

fumaric acid, itaconic acid, maleic acid. The metals for neutralisation

include, e.g. Na, K and Li. Waxes comprising mainly higher <u>fatty</u> <u>acid</u> esters

such as polyethylene wax, carnauba wax, etc. are pref. The aq.

3/13/06, EAST Version: 2.0.3.0

codispersions

are obtd. e.g. by adding the aq. dispersion of the copolymers to wax emulsions,

and stirring the mixts., or kneading. Components (1) and (2) previously in

kneaders, etc. and forming the aq. dispersions of the mixt.

The present dispersions are pref. used for coating of cellophane, aluminum

foil, and they are applied to synthetic films or sheets (e.g. nylon, polyvinyl

chloride, polypropylene) in order to impart oil resistance, heatsealing

property and adherence.

TITLE-TERMS: AQUEOUS COATING DISPERSE HEAT SEAL ANTIBLOCKING COMPRISE COPOLYMER

POLYETHYLENE UNSATURATED CARBOXYLIC ACID SALT FORM WAX

DERWENT-CLASS: A17 A60 A82 G02

CPI-CODES: A04-F04; A04-F05; A04-G08; A12-B04D; A12-B04F; A12-B07; G02-A02C;

G02-A02D; G02-A02D3;

POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:

Key Serials: 0037 0041 0044 0047 0209 0218 0231 0239 0241 0248 0759 1283 1982

1989 2001 2022 2335 2375 2430 2433 2437 2439 2504 2511.2513 2522 2570 2608 2656

2659 2718 2726 2728 0411 1424 1431 1417

Multipunch Codes: 011 034 04- 040 041 046 047 050 06- 061 062 063 074 075 076

09& 09- 10& 141 230 231 24- 250 252 253 259 27& 323 392 397 423 431

435 436 443

47& 475 477 502 532 533 534 541 548 597 600 688 724 011 034 04- 040

041 046 047

050 06- 061 062 063 075 09& 09- 10& 104 107 141 155 157 230 231 24-

250 252 253

259 27& 323 392 397 423 431 435 436 443 47& 475 477 502 532 533 534

541 548 597

600 688 724 011 034 04- 040 041 046 047 050 06- 061 062 063 075 09&

09- 10& 104

116 141 155 157 230 231 24- 250 252 253 259 27& 323 392 397 423 431

435 436 443

47& 475 477 502 532 533 534 541 548 597 600 688 724 011 034 04- 040

041 046 047

050 06- 061 062 063 075 09& 09- 10& 104 105 141 155 157 230 231 24-

250 252 253